



AB-266

GRADE	Industrial
FINISH	Smooth
POWDER	No
TRIMMED	Yes
COLOR	White

TECHNICAL SPECIFICATIONS

SPECIFICATION ASTM D2000: 1BC612Z1 Z1= HARDNESS 55 +/- 5 SHORE A | POLYMER: NEOPRENE (CR) BLEND

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.55
D2240	HARDNESS (shore A)	55 +/-5
D412	TENSILE (psi)	1200 min.
	ULTIMATE ELONGATION (%)	300 min.
D395B	COMPRESSION SET	22 hrs @ 100°C (212°F) 80% max.
D573	HEAT AGING	70 hrs @ 100°C (212°F) Changed Hardness: +/-15 points max. Tensile: +/-30% max. Elongation: -50% max.
D471	FLUID RESISTANCE OIL #3	70 hrs @ 100°C (212°F) Changed in volume: 120% max.
TEMPERATURE RANGE (general guideline)		-20° to 190°F (-29° to 88°C)

Maximum pieces per roll: 2

Minimum piece length: 10'

Width tolerance: -0 / +1"

Material is within commercial sheet rubber gauge tolerances.

Please ensure the product meets your application specification prior to order placement.

Specifications are subject to change without notice. The website version prevails.

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
25A-04-482 ¹	1/16 (1.60)	48 (1219.2)	400 (37.16)	100 (30.48)	175 (79.4)
25A-08-482	1/8 (3.20)	48 (1219.2)	200 (18.58)	50 (15.24)	175 (79.4)
25A-12-482 ¹	3/16 (4.80)	48 (1219.2)	160 (14.86)	40 (12.19)	205 (93.0)
25A-16-482 ¹	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	292 (132.4)

¹ Made to order.